Product Data Sheet

RIVETONE CLEAN PLUS G12

Coating that combines the breathability characteristic of the siloxane component with an oxidative photocatalytic effect capable of decomposing the organic substances that come into contact with the surface. Particularly suited for finishing the major TERMOK8 systems. For outdoor use.

DESCRIPTION

This self-cleaning effect is achieved as a result of functionalization through nanometre technology using UV rays, water and oxygen. Dirt, pollutants, and microorganisms thus eradicated will be washed away at the first rain, and the substrate will remain, therefore, as white as it was originally. Produces a mould-, algae-, and fungi-resistant film, using an innovative formulation based on broad spectrum additives, effective even under the most critical weather and environmental conditions and certified by the FRAUNHOFER- INSTITUT FÜR BAUPHYSIK of Munich.
For professional use

MAIN PROPERTIES

- Self-cleaning
- Photocatalytic effect
- Breathable
- Low absorption
- Compact effect

TECHNICAL DATA

Classification UNI 8681	Plastic coating for continuous application - natural granules - G2 - Skimmed - R2 - S2
Film aspect EN 13300	Matt G3 (≤ 10 gloss 85°)
Maximum granulometry EN 1062	1.2mm
Specific weight	1850 ± 100 g/l
pH	7-9
Type of binder	Acrylic-siloxane
Solid content	81 ± 2 %
Vapour permeability EN 1062	Class V1 - High
Water absorption EN 1062	Class W3 Low
Strength adhesion EN 1542	> 1.5 MPa
Thermal conductivity EN 1745	λ=0,85 W/(mK)
Drying time	Under standard environmental conditions, it can be overpainted after 24 hours. In case of low temperatures or high humidity, drying times can vary considerably.
VOC	Cat A/c: limit 40 g/l (2010) This product contains a maximum of 40 g/l of VOCs

CHARACTERISTICS

Colour range	White and selected Colours can be achieved with the You Color tinting system
Coverage	With the application of 1 coat: 2 Kg/m2
Coverage per pack	(25Kg): 12.5 m2, approx. Coverage varies according to the roughness of the substrate.
Dilution	ready to use; add a little water if necessary to achieve the right consistency

Product Data Sheet

Diluted with	Water
Overpaintable	Compatibility with other products: compatible with all water-based products

APPLICATION

Suitable Substrates:
Cement-based Render, painted plaster, lime-based plaster and paint, exposed reinforced concrete, precast concrete features and panels, gypsum and fibre cement walls and features.
Preparation of the Substrate:
All substrates must be free of release agents and must be dry, clean and coherent. Renders must be sufficiently cured according to the type of material and manufacturer's instructions. In the case of old paint or dusty substrates, we recommend applying a coat of PRIMACRIL (IVAS) consolidating primer or removing them if this is not sufficient.
Application Procedure:
Mix using a low speed mixer. Apply RIVATONE CLEAN PLUS G12 with a metal trowel to achieve a uniform, continuous layer. When the layer is not dry (after about 5 minutes, depending on the weather conditions), finish with a plastic trowel with rotary movements to achieve the desired aesthetic effect.
Type of Equipment:
metal trowel, plastic trowel
Notes:
Do not apply when in direct sunlight or when it is very windy. Delay in drying during the initial period of exposure to the weather can form unsightly streaks on the surface due to condensation, fog or rain. Depending on the intensity of the colour, this effect may be more or less evident but does not imply any reduction in product quality. As a rule, these imperfections disappear on their own upon additional exposure to heavy rainfall.
Ambient Conditions:
min +5°C max +35°C max RH 80%

STORAGE

Tub Size:
25 Kg
Ambient Conditions:
1 year when stored in undamaged packages at between 5 and 30°C; cannot endure frost and direct sunlight
Dispose of in accordance with local regulations.
For information on possible hazards, refer to the safety data sheet